


Product comparison : Koru KIR versus Fuji HRD

System Features Octagon

Based on Agfa Proset 9800 tests



Review + implementation

● IR 780 nM/ drop-in for :

- ◆ processing set-up

Adjustment for :

- ◆ calibration set-up : needs to be adjusted
- ◆ exposure set-up: output an internal test exposure
: based on a practical density of 4.10 a decline in exp. of +- 10% is needed.

Product Colors

KIR



Emulsion side

Back side

HRD



Emulsion side

Back side





KIR

Product comparison : Koru KIR versus Fuji HRD

Image quality



2400 dpi / 150 lpi

Koru KIR		Fuji HRD	
On Agfa Proset 9800 (IR 780nM)			
			
50% = 56%	5% = 6%	50% = 54%	5% = 3%

Practical Photographic Properties

Engine	Agfa Proset 9800			
	KIR	HRD		
Property	KIR	HRD		
Int. Setting	95	85		
Practical density	D.4.10- 4.30	D.4.10- 4.30		
5%	6%	4%		
50%	60%	51%		
95%	99%	97%		

Note: - Koru KIR processed in Koru KF dev. - Fuji HRD processed in Fuji QR-D1
 - Before switching over to Koru KF developer cleansing with Koru Chemical Cleaner is obligatory.