


## Product comparison : Koru KRD versus Agfa HNS

### System Features Octagon

Based on Screen Katana tests



### Review + implementation

● **HeNe 635 nm/ drop-in for :**

- ◆ processing set-up
- ◆ calibration set-up

**Adjustment for :**

- ◆ exposure set-up : output an internal test exposure  
: based on practical density of 4.00 an increase in exp. of +- 35% is needed

● **HeNe 650 nm/ drop-in for :**

Identical

**Adjustment for :**

- ◆ exposure set-up : output an internal test exposure  
: based on practical density of 4.00 an increase in exp. of +- 15% is needed

### Product Colors

#### KRD



Emulsion side

Back side

#### HNS



Emulsion side

Back side

# Koru KRD

## Product comparison : Koru KRD versus Agfa HNS

Image quality



2400 dpi / 150 lpi

Koru KRD		Alliance HNS	
<b>On Screen Katana</b>			
50% = 54%	5% = 4%	50% = 54%	5% = 4%
<b>On Agfa Avantra</b>			
50% = 52%	5% = 5%	50% = 52%	5% = 5%

### Practical Photographic Properties

Engine	Screen Katana		Agfa Avantra	
	KRD	HNS	KRD	HNS
Property				
<b>Int. Setting</b>	205	165	260	230
<b>Practical density</b>	D.4.00-4.10	D.4.00-4.20	D.4.00-4.10	D.4.10-4.30
<b>5%</b>	4%	3%	5%	4%
<b>50%</b>	59%	57%	56%	53%
<b>95%</b>	99%	99%	96%	95%

Note: - Koru KRD processed in Koru KF developer - Agfa HS processed in Agfa G101c.  
 - Before switching over to Koru KF developer cleansing with Koru Chemical Cleaner is obligotary.